

bandit1100@126.com

Arrived: 09 Jul 2015 Completed: 28 Jul 2015



# **Test Report**

Shandong Yeliya Garment Group Co., Ltd

## Hortobagyi White Goose Down 95%

28 Jul 2015

**Mao Bandit** 

Shandong Yeliya Garment Group Co., Ltd

591 Wolong Str. Weifang City **CHINA** 

Sample Description: Plumage **Shipped By:** STO 868443333963

**Filling Label:** 

Sample Identification: Hortobagyi White Goose Down 95%



This analysis represents (within normal testing variances) the test results from the sample(s) submitted. The analysis may not represent the entire lot, batch or production run. In no event shall IDFL be responsible or liable for any direct, indirect, punitive, incidental, special, or consequential damages whatsoever arising out of or connected with the use of, misuse of, or reliance upon such results or analysis. This test report is subject to the Terms and Conditions found at



IDFL 1455 South 1100 East Salt Lake City, UT 84105 USA Tel: +1 801 467 7611

email: info@idfl.com

IDFL EUROPE Zürcherstrasse 282 CH-8500 Frauenfeld Switzerland Tel: +41 52 765 1574 email: europe@idfl.com IDFL CHINA Tonghui Mid-Road 118, Xiaoshan, Hangzhou Zhejiang 311208

China Tel: +86 571 8273 6561 email: china@idfl.com

IDFL TAIPEI 3F/4F., No. 163, Sec. 2, Wenhua Rd., Banqiao District, New Taipei City

Taiwan Tel: +886 2 2259 1178 email: taiwan@idfl.com www.idfl.com Page: 1 of 2 Client: 9449

XS

Sample: 3 of 3







# **Test Report**

Shandong Yeliya Garment Group Co., Ltd

## Hortobagyi White Goose Down 95%

28 Jul 2015

### Content Analysis GB/T 14272-2011 Method

**Down Cluster** 90.8%

**Down Fiber** 3.0%

Feather Fiber 1.4%

**Waterfowl Feathers** 4.6%

**Broken / Damaged Feathers** 0.0%

**Quill** 0.0%

Landfowl 0.2%

Residue 0.0%

**Long Feathers** 0.0%

**Total** 100.0%

**Total Down (Down Cluster + Down Fiber)** 93.8%

## **Species GB/T 14272-2011**

Goose Down 81%

**Duck Down** 19%

**Goose Feathers** 76%

**Duck Feathers 24%** 

**Total Goose** 81%

**Total Duck 19%** 

### **Fill Power**

Method	Conditioning	Final
IDFB/Lorch Cylinder (in³/30g)	Steam IDFB-10-B	825

### **Cleanliness Evaluation**

**Turbidity GB/T 14272-2011** 1000+ mm **IDFB-11** 1.10 NTU

This analysis represents (within normal testing variances) the test results from the sample(s) submitted. The analysis may not represent the entire lot, batch or production run. In no event shall IDFL be responsible or liable for any direct, indirect, punitive, incidental, special, or consequential damages whatsoever arising out of or connected with the use of, misuse of, or reliance upon such results or analysis. This test report is subject to the Terms and Conditions found at www.idfl.com.



Security # 3371664948 e-Signature

IDFL 1455 South 1100 East Salt Lake City, UT 84105 USA Tel: +1 801 467 7611 email: info@idfl.com IDFL EUROPE Zürcherstrasse 282 CH-8500 Frauenfeld Switzerland Tel: +41 52 765 1574 email: europe@idfl.com

IDFL CHINA Tonghui Mid-Road 118, Xiaoshan, Hangzhou Zhejiang 311208 China Tel: +86 571 8273 6561

email: china@idfl.com

IDFL TAIPEI 3F/4F., No. 163, Sec. 2, Wenhua Rd., Banqiao District, New Taipei City Taiwan Tel: +886 2 2259 1178 email: taiwan@idfl.com www.idfl.com Page: 2 of 2 Client: 9449 XS

Sample: 3 of 3